# **Trimount**

# TECHNICAL SPECIFICATION

Trimount<sup>™</sup> is a 2.6 mil (65µ) pH-neutral white mounting tissue, coated on both sides with a heat-activated solvent acrylic adhesive that is tackfree at normal ambient temperature and does not require a release liner.

- FOR USE IN ALL TYPES OF DRY MOUNTING PRESSES
- RECOMMENDED FOR BONDING RESIN-COATED PHOTOGRAPHIC PAPER AND PRINTED MATERIALS TO SMOOTH SURFACES
- THIS ADHESIVE HAS EXCELLENT LONG-TERM STABILITY AND WILL NOT NEGATIVELY IMPACT ANY COMPATIBLE SUBSTRATE OR MEDIA IN LONG-TERM APPLICATIONS UNDER NORMAL STORAGE CONDITIONS.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2023 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

## PRODUCT STRUCTURE

| Adhesive | Solvent Acrylic (Heat Activated) |
|----------|----------------------------------|
| Film     | Off White Kraft Paper            |
| Adhesive | Solvent Acrylic (Heat Activated) |

### PRODUCT CHARACTERISTIC

| Paper Weight              | 50 gsm 3.6 mil   |  |
|---------------------------|--|--|
| Adhesive Layer            | 0.5 mil (12μ) on each side (89μ)                           |  |
| Film/Adhesive Ratio       | 0.5:2.6:0.5  |  |
| UV Protection Factor      | Not Applicable   |  |
| Outdoor Durability        | Not Applicable   |  |
| Service Temperature Range | -4°F to 203°F (-20°C to 95°C)                              |  |
| Shelf Life                | 2 Years  |  |
| Storage Conditions        | 59°F to 72°F (15°C to 22°C);<br>50 - 55% Relative Humidity |  |

### PROCESS SETTINGS

| Equipment Type & Temperature                     | Speed           |
|--|-----------------|
| Roller Laminator Not Recommended                 | Not Recommended |
| <b>Press</b><br>194°F to 210°F<br>(90°C to 99°C) | 60 - 90 seconds |



#### **Europe**

Filwood Road, Fishponds, Bristol, BS16 3RY, United Kingdom bristol@drytac.com Tel: +44 (0) 117 958 6500

#### Canada

30 Driver Road, Brampton, Ontario, L6T 5V2, Canada toronto@drytac.com Tel: +1 800.353.2883

# S

**USA** 

5401 B Eubank Road, Sandston, Virginia, 23150, USA customerservice@drytac.com Tel: +1 800.280.6013