

Protac™

Scribe™

Protac™ Scribe™ is a 2 mil (50µ) phthalate-free, biaxially-oriented PP laminating film with a gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with a siliconized PE.

- SUITABLE FOR APPLICATION TO HEAT SENSITIVE OUTPUT AND HIGH INK COVERAGE IMAGES PRINTED ON PHOTO GLOSS PAPER
- IDEAL FOR DRY ERASE PRESENTATION BOARDS, SCHEDULES, YEARLY PLANNERS, OR MAPS.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2023 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

| | |
|----------------------|--------------------------------------|
| Film | Gloss Clear PP |
| Adhesive | Aqueous Acrylic (Pressure Sensitive) |
| Release Liner | Siliconized 1 Side PE Coated Kraft |

PRODUCT CHARACTERISTIC

| | |
|-------------------------------------|--|
| Film Thickness | 2 mil (50µ) 3 mil |
| Adhesive Layer | 1 mil (25µ) (75µ) |
| Film/Adhesive Ratio | 2:1 |
| UV Protection | Yes |
| Outdoor Durability | Not Applicable |
| Service Temperature Range | -4°F to 230°F (-20°C to 110°C) |
| Peel Strength (20 min, FTM1) | 11 N/25mm |
| Shelf Life | 2 Years |
| Storage Conditions | 59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity |

PROCESS SETTINGS

| Equipment Type & Temperature | Speed |
|---|--|
| Roller Laminator Room temperature to 104°F (40°C) | 1 ft to 8 ft (0.3m to 2.5m) per minute |
| Press | Not recommended |

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013

www.drytac.com