UltraTac™

TECHNICAL SPECIFICATION

UltraTac™ is a 0.5 mil (12µ) clear PET high tack, high bond strength fi lm, coated on both sides with a pressure sensitive acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with siliconized PE. The adhesive is self-wound on the release liner.

● ULTRATAC[™] IS A HIGH GRADE VERSION OF MEDIATAC[™], SUITABLE FOR ALL THE SAME APPLICATIONS AND DESIGNED FOR MOUNTING GRAPHICS ONTO MORE DIFFICULT SUBSTRATES, SUCH AS FOREX[™], MDF, GATORBOARD[™], ULTRABOARD[™], FOAMEX[™], OR SINTRA[™].

PRODUCT STRUCTURE

Adhesive	Acrylic (Pressure Sensitive)	
Film	Clear PET	
Adhesive	Acrylic (Pressure Sensitive)	
Release Liner	2 Side PE Coated, 2 Side Siliconized Kraft	

PRODUCT CHARACTERISTIC

Film Thickness	0.5 mil (12µ)	
Adhesive Layer	1.1 mil (28µ) on each side 4.4 mil	
Film/Adhesive Ratio	1.1:0.5:1.1 (109 _µ)	
UV Protection Factor	Not Applicable	
Outdoor Durabilty	Not Applicable	
Service Temperature Range	-4°F to 248°F (-20°C to 120°C)	
Shelf Life	2 years	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

PROCESS SETTINGS

Equipment Type $\&$ Ter	nperature	Speed
Roller Laminator Room temperature to 104°F (40°C)		1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not rec	ommended



For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

Europe

Filwood Road, Fishponds, Bristol, BS16 3RY, United Kingdom bristol@drytac.com Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court, Brampton, Ontario, L6T 5A9, Canada toronto@drytac.com

Tel: +1 800.353.2883

USA

5601 Eastport Boulevard, Richmond, Virginia, 23231, USA customerservice@drytac.com

Tel: +1 800.280.6013